



Plus ThB

Intumescent Coating

Spray Polyurethane Foam Insulation

MANUFACTURER

No-Burn, Inc.
1255 High Street, Suite 200
Wadsworth, Ohio 44281
www.noburn.com

DESCRIPTION

No-Burn Plus ThB is a water-based thin film intumescent coating when exposed to high temperatures and flame, intumesces creating a char-barrier protecting treated Substrates from fire.

1. PRIMARY USES

For use in new and existing buildings, complying with the IBC, IMC, IRC, IEBC and other applicable codes or standards, Plus ThB is utilized in applications where it provides:

- Interior Finish Classification Class I or Class A: FS 0 / SD 10
Alternative or Non-prescriptive Thermal Barrier
Alternative or Non-prescriptive Ignition Barrier
Class III Vapor Retardancy
Exterior Rated Wall Assembly

Code Compliance Evaluation Reports: ER 305 & TER 1905-03.
Installation Verification: SPFA-148.
Intertek Design Listing: BASF/FI 30-09.

2. SPECIFICATIONS

Table with 2 columns: Specification and Value. Includes Color (White/Gray/Tinted), Finish (Flat), VOC Content (18 g/L), Dry Time (60-90 Minutes), Pails (5 Gallons), Drums (55 Gallon Drum), Shelf Life (12 Months), Cure Time (24 Hours), Boiling Point (212°F), Freezing Point (32°F), % Volatile by Volume (33%), Specific Gravity (1.25).

View product Safety Data Sheet (M)SDS and Best Practices for Safe Handling & Storage for more information.

3. PRODUCT PERFORMANCE

No-Burn Plus ThB may be used for the Primary Uses expressed. As a component in an alternative ignition barrier assembly or thermal barrier assembly, Plus ThB is an intumescent fire protective coating for interior spaces where spray polyurethane foam is installed.

requirements for incidental food contact and ANSI/NSF 51 Food Zone Materials.

4. APPLICABLE STANDARDS

- No-Burn Plus ThB may be specified in compliance of the following:
AC377 EC017
AC456 GSA PBS-P100
ANSI/ASHRAE/ICC/USGBC Standard 189.1 ICC/ASHRAE 700 NGBS
ANSI/NSF 51 IgCC
ASTM E84 LEED v3 2009 & v4
ASTM E96 NFPA 285
CARB NFPA 286
CDPH (CA Spec 01350) SCAQMD Rule 1113
CHPS UL 1715

Table 1: Material vs Substrate. Columns: Material, TB1 or IB2, Film Thickness, Spread Rate. Lists various foam materials and their compatibility with different substrates.

1 Alternative Thermal Barrier (TB) Assemblies; Evaluation Reports: ER 305 Table 2 & TER 1905-03 Table 1.

2 Alternative Ignition Barrier (IB) Assemblies; Evaluation Reports: ER 305 Table 3 & TER 1905-03 Table 2.



Made in the USA



Technical Data Sheet

Table 1 Continued

Material	Substrate		
	TB <sup>1</sup> or IB <sup>2</sup>	Film Thickness	Spread Rate
Foam Supplies genfoam Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Foam Supplies genX Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Foam Supplies ecostar Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Gaco EZSpray F4500 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Gaco F183M Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Gaco OnePass F1850 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Gaco OnePass 1860 HFO SPF	TB	14 wet	115 sq. ft./gal.
Gaco OnePass Low GWP F1880 SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 050 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 050 Max Pro Open Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 050 Max Open Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 050X Open Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 170 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 202 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 202 High-Lift Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 202 Max Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 205 HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
General Coatings Ultra-Thane 205 HFO High-Lift CC SPF	TB	14 wet	115 sq. ft./gal.
Genky Elite 2.0 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Demilec) Sealection® 500 Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Sealection® NM Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Agribalance® Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) APX 1.2 Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok HFO High Lift Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok HFO Pro Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok XT-s Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok XT-w Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok ECO Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Demilec) Heatlok HFO EZ Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) Classic Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Select Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) Classic Plus Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) Prime Gold Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) No Mix Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) ProSeal Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) ProSeal LE Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) ProSeal Eco Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) ProSeal HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) ProSeal HFO CW Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Icynene) MD-C-200 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 450 Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 500 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 750 Open Cell SPF	TB	16 wet	100 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 2000-3G Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 2000-4G Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 2000 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
ICP Handi-Foam HVLP LD Open Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
ICP Handi-Foam HVLP MD Closed Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond HY Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond OCX Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond III Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond IV Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM GEN IV Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Johns Manville JM Corbond MCS Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Natural Polymers Natural-Therm Zero Closed Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
Natural Polymers Natural-Therm 2.0 Closed Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
Natural Polymers Natural-Therm 2.0 HFO Closed Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
Natural Polymers Ultra-Pure Closed Cell Spray Foam	TB	14 wet	115 sq. ft./gal.
NCFI InsulStar Light 12-008 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
NCFI InsulStar Light 12-075 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
NCFI InsulStar 11-033 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
NCFI InsulStar 11-036 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
NCFI InsulBloc 11-037 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
NSF Polymers CC OG HFC Closed Cell SPF	TB	14 wet	115 sq. ft./gal.

Table 1 Continued

Material	Substrate		
	TB <sup>1</sup> or IB <sup>2</sup>	Film Thickness	Spread Rate
NSF Polymers R-Max Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Nu-Wool Nu-Seal 0.5 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Nu-Wool Nu-Seal 2.0 HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Nu-Wool Nu-Seal Plus Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
PSI Staycell 505 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
PSI Staycell 508 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
PSI Staycell 504-2 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Quadrant Performance EnviroSeal HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SES EasySeal 0.5 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
SES SucraSeal 0.5 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
SES Nexseal 2.0 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SES Nexseal 2.0 LE Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 108 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 108YM Open Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 112XC Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 118 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 133 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield 144 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
SWD Quik-Shield YETI Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
ThermoSeal 2000/2000W Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
ThermoSeal TS HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
ThermoSeal OCX Open Cell SPF	TB	16 wet	100 sq. ft./gal.
ThermoSeal CCX Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
ThermoSeal 5G Closed Cell SPF	TB	14 wet	100 sq. ft./gal.
UPC 500 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 500 Classic Open Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 500 Max Open Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 500 Max Pro Open Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 500 OCX Open Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 1.7 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 2.0 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 2.0 HL Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 2.0 MAX Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 2.0 HFO Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
UPC 2.0 HFO High Lift Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Victory Polymers VPC-50 Open Cell SPF	TB	14 wet	115 sq. ft./gal.
Victory Polymers VPC-CC SuperLift Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Victory Polymers VPC-CC SuperYield Closed Cell SPF	TB	16 wet	100 sq. ft./gal.
Xcelus XLS 200 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
Xcelus XLS 2000 Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
XtremeSeal 0.4 LX Open Cell SPF	TB	14 wet	115 sq. ft./gal.
XtremeSeal 0.5 LX Open Cell SPF	TB	14 wet	115 sq. ft./gal.
XtremeSeal 2.0 LE Closed Cell SPF	TB	14 wet	115 sq. ft./gal.
AMBIT AMBI-SEAL 5.0 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Alpha Polymers AP 100 (OC) Open Cell Foam	IB	6 wet	267 sq. ft./gal.
BASF Enertite® G Open Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Enertite® Max Open Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® 158 Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® SP Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® Comfort Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® Comfort XL Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® LWP-L Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Spraytite® 178 Closed Cell SPF	IB	12 wet	134 sq. ft./gal.
BASF Spraytite® 81206 Closed Cell SPF	IB	12 wet	134 sq. ft./gal.
BASF Walltite® US Closed Cell SPF	IB	12 wet	134 sq. ft./gal.
BASF Walltite® LWP Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Walltite® MAX Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Walltite® XL Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
BASF Walltite® Plus Closed Cell SPF	IB	6 wet	267 sq. ft./gal.
Carlisle SealTite Pro Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Carlisle Foamsulate 50 HY Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Carlisle SealTite Pro High Yield Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Carlisle SealTite Pro XTR Open Cell SPF	TB	6 wet	267 sq. ft./gal.
Carlisle Foamsulate 50 ES Open Cell SPF	TB	6 wet	267 sq. ft./gal.

<sup>1</sup> Alternative Thermal Barrier (TB) Assemblies; Evaluation Reports: ER 305 Table 2 & TER 1905-03 Table 1.

<sup>2</sup> Alternative Ignition Barrier (IB) Assemblies; Evaluation Reports: ER 305 Table 3 & TER 1905-03 Table 2.



Made in the USA



Table 1 Continued

Material	Substrate		
	TB <sup>1</sup> or IB <sup>2</sup>	Film Thickness	Spread Rate
Carlisle Foamsulate 50 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Carlisle SealTite Pro No Mix Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Creative Polymer Accufoam® Open Cell SPF	IB	6 wet	267 sq. ft./gal.
DAP Touch N' Seal 2.2.PCF Closed Cell SPF	IB	8 wet	200 sq. ft./gal.
Franklin Titebond Weathermaster Superfoam Closed Cell SPF	IB	10 wet	160 sq. ft./gal.
Gaco EZspray F4500 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Holcim SES EasySeal ULD Spray Foam Insulation	IB	6 wet	267 sq. ft./gal.
Huber ZIP Systems R-Sheathing Panel (R-3 & R-6)	IB	10 wet	160 sq. ft./gal.
Huntsman (Demilec) Sealection® 500 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Demilec) Sealection® NM Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Demilec) Agribalance® Open Cell SPF	IB	10 wet	267 sq. ft./gal.
Huntsman (Icynene) Classic Plus Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Icynene) Classic Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Select Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Icynene) Prime Gold Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Icynene) MD-C-200 Closed Cell SPF	IB	16 wet	100 sq. ft./gal.
Huntsman (Icynene) ProSeal Eco (MD-R-200) Closed Cell SPF	IB	5 wet	320 sq. ft./gal.
Huntsman (Lapolla) FL 450 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
Huntsman (Lapolla) FL 750 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
ICP Handi-Foam HVLP LD Open Cell Spay Foam	IB	6 wet	267 sq. ft./gal.
ICP Handi-Foam® E-84 Class 1(A) Closed Cell Spray Foam	IB	10 wet	267 sq. ft./gal.
John Manville JM Corbond HY Open Cell SPF	IB	6 wet	267 sq. ft./gal.
NSF Polymers OC-OG Open Cell SPF	IB	6 wet	267 sq. ft./gal.
NSF Polymers OC Open Cell SPF	IB	6 wet	267 sq. ft./gal.
SES EasySeal ULD Open Cell SPF	IB	6 wet	267 sq. ft./gal.
SES EasySeal 0.5 Open Cell SPF	IB	5 wet	320 sq. ft./gal.
SWD Quik-Shield 106 Open Cell SPF	IB	6 wet	267 sq. ft./gal.
ThermoSeal TS 360 Open Cell Spray Foam	IB	4 wet	401 sq. ft./gal.
ThermoSeal TS 500 Open Cell Spray Foam	IB	4 wet	401 sq. ft./gal.
ThermoSeal TS 800 Open Cell Spray Foam	IB	4 wet	401 sq. ft./gal.
ThermoSeal OCK Open Cell Spray Foam	IB	6 wet	267 sq. ft./gal.
Tiger Foam® E-84 Fire Rated Class 1 SPF	IB	10 wet	160 sq. ft./gal.
Victory Polymers VPC-50 Open Cell SPF	IB	6 wet	267 sq. ft./gal.

<sup>1</sup> Alternative Thermal Barrier (TB) Assemblies; Evaluation Reports: ER 305 Table 2 & TER 1905-03 Table 1.

<sup>2</sup> Alternative Ignition Barrier (IB) Assemblies; Evaluation Reports: ER 305 Table 3 & TER 1905-03 Table 2.

## 5. EQUIPMENT

Methods of application include airless sprayer, roller or brush. Manufacturers and models of airless spray *Equipment* vary and examples of applicable *Equipment* follow. Airless spray *Equipment* recommendations have been linked for reference to manufacturer specifications.

Table 2		
Equipment		
Manufacturer	Model	
Graco®	<a href="#">Ultra Max II 795</a>	<a href="#">Ultra Max II 1595</a>
	<a href="#">Ultra Max II 1095</a>	<a href="#">TexSpray Mark V</a>
Titan®	<a href="#">Impact™ 840</a>	<a href="#">PowrTwin™ 6900 Plus</a>
	<a href="#">Impact™ 1140</a>	<a href="#">PowrTwin™ 8900 Plus</a>
Recommended tip orifice sizes of .019 - .025 and airless sprayer hoses inside diameter of ¼" or larger.		

Spray *Equipment* must be capable of producing a minimum of 3,300 psi, and recommended tip sizes are 419-425 or 519-525. Removal of filter from the spray gun to allow for the passage of solid content is recommended. Do not remove the rock guard (screen) from the bottom of the intake tube. Airless sprayer hoses are recommended to have an inside diameter of ¼" or larger. Variations in spray pattern width and tip size may be required depending on the surface area and the *Substrate(s)* to which Plus ThB is being applied. Cleanup of *Equipment* may be with

water, or other methods recommended by the *Equipment* manufacturer.

## 6. PERSONAL PROTECTION & EXPOSURE CONTROLS

Wearing a certified respirator and goggles to avoid overspray and splashing are recommended. Eye and face protection should be in accordance with OSHA 29 CFR 1910.133. Rubber or plastic gloves are recommended for hand and arm protection. Personal cleanup may be with soap and water. If sprayed, wear an air-purifying respirator approved by NIOSH in accordance with OSHA 29 CFR 1910.134(d)(1)(ii). If used in a confined area, a full-face, powered air-purifying respirator (PAPR) or supplied-air respirator (SAR) is recommended. Use respirators in accordance with 29 CFR 1910.134(d)(3)(i)(A) Table 1, 29 CFR 1910.134(d)(3)(iii)(B) and 29 CFR 1910.134(d)(3)(iv)(B).

Use appropriate engineering controls, such as proper ventilation. Where such systems are not effective, wear suitable personal protective equipment, which performs satisfactorily and meets OSHA or other recognized standards.

## 7. MIXING, TINTING, OVERCOATS & UNDERCOATS

Plus ThB must be thoroughly mixed before use in accordance with the manufacturer's recommendations. Mix with a 5 gallon power mixing wand at or between 800-1200 RPM until thoroughly mixed. Shaking No-Burn® Plus ThB with a paint shaker is NOT sufficient. Filtering or straining Plus ThB is not recommended. If No-Burn® Plus ThB is mixed more than 24 hours prior to use, mix it again according to manufacturer's instructions.

Thinning is usually not needed; if Plus ThB has been exposed to high heat, water may evaporate from the plastic 5 gallon container. If the paint level is below 3-4 inches from the top of the container, add enough water to bring the level back up to within 3 inches from the top in order to ensure proper consistency. Mix Plus ThB again according to manufacturer's instructions.

After mixing, if the viscosity is still too high, you may add 8 ounces of water per 5 gallon pail and mix to reduce the viscosity. Mix Plus ThB again according to manufacturer's instructions. Use Caution not to add too much water or the product may run and drip during application.

Plus ThB should never be allowed to freeze 32°F (0°C), stored between 40°F and 90°F (4.4°C and 32.2°C), and kept out of direct sunlight; if you cannot verify that these conditions have been maintained, the product may be disposed of in accordance with the manufacturer's (M)SDS.

If tinting is desired, Plus ThB may be tinted at a maximum rate of 2 oz. of tint per gallon with commercially available tint that is safe to be used with water-based paints. It is recommended that No-Burn® Black Tint, manufactured by No-Burn, Inc., be used for tinting. No-Burn® Black Tint can be added at a rate of 12oz per 5-gallon pail. Contact the manufacturer for additional tinting information.

When a specified or black color is desired, an overcoat may be used and shall be water-based with a pH of 7-8 (i.e., Sherwin Williams A-100 or Behr Premium Plus). Prior to the use of any overcoat, it is recommended that an inconspicuous area be tested for compatibility before widespread application. Compatibility may be noted as the overall satisfactory condition of the *Substrate(s)* once No-Burn® Plus ThB and an



overcoat have been applied. No-Burn® Inc. makes no guarantees of color matching when using a tint from a third-party manufacturer.

### 8. APPLICATION

When applying No-Burn® Plus ThB, the coating shall be applied to *Substrate(s)*, as applicable, in accordance with Evaluation Report (ER) 305, Evaluation Report (TER) 1905-03 and/or manufacturer’s technical data sheet/instructions. Copies of relevant technical data and/or documents shall be available at the jobsite.

Before and during coating application, the *Substrates’* surfaces shall be dry, clean and free from loose debris, dust, dirt, grease, oil, and all prior coating materials, such as paint, stains and sealers. The foam should be allowed to cool to ambient room temperature prior to the application of No-Burn® Plus ThB, minimum 1 hour. The *Substrate(s)* shall not have, nor have been exposed to, treatments, chemicals, coatings, etc. prior to the application of Plus ThB. Visual observation of the intumescent coating is naturally and distinctively white in color. For verification of the wet applied thickness, a standard painter’s thickness gauge shall be used during the application. The finished dry mil thickness will be 0.55-0.70 times the wet mil thickness.

*Substrate(s)* shall be in the final position in the building, directly exposed to the interior, protected from the weather, in conditioned and unconditioned locations. Furthermore, Plus ThB shall be applied to areas within the weatherproofing membrane or surfaces not exposed to weather.

Surface and ambient temperatures before and during application shall be 40°F (4.4°C) minimum. Surface temperatures shall not exceed 100°F (37.7°C) during application. The coating shall be applied at an application rate set forth by spraying, roller or brush. Dry time is typically 60-90 minutes and cure time is typically 24 hours minimum, depending on the ambient temperature and relative humidity conditions. If more than one coat is required, allow No-Burn® Plus ThB to dry completely between coats.

It’s always best to follow SPF Manufacturer guidelines first and foremost when it comes to installing Plus ThB, following the spray installation instructions closely. For high heat, humidity or extreme cold, Plus ThB installation guidelines are as follows.

- A. Plus ThB can be installed to newly installed SPF based upon the top coat times of the SPF manufacturer. Please refer to the technical data information of the SPF that Plus ThB will be applied to. Follow the installation instructions of the SPF manufacturer closely.
- B. Ideal installation temperatures are 65 degrees Fahrenheit or above, and less than 65% relative humidity.
- C. Ambient air and substrate temperature MUST be above 40 degrees Fahrenheit to apply Plus ThB and cannot drop below 40 degrees Fahrenheit until after Plus ThB has dried to the touch.
- D. For at least 72 hours after installation of Plus ThB, consistent temperatures must be maintained within the installation parameters (at least 40 degrees Fahrenheit, preferably 65 degrees Fahrenheit or above) and no more than a 65% relative humidity with readings taken daily. Any conditions outside of these guidelines must be approved by No-Burn®, Inc. technical service.
- E. The space where Plus ThB is being installed must be well ventilated, either by natural openings or with the use of mechanical ventilation equipment, both during installation and for up to 72 hours once installation is complete, to allow for the curing process to complete. Humidity of the ambient air and amount of airflow through the space may affect cure times (i.e. more humid with less air movement may take more time to cure).
- F. Once cured, Plus ThB installed in continuous high humidity environments will require a top coat such as Behr Premium Plus or Sherwin Williams A-100 exterior paint (i.e.: 70% humidity and higher.). Parking structures, both above and below grade, will require this protection. If the installer has any questions regarding the humidity levels of the environment once Plus ThB is installed, it is recommended that they discuss with a No-Burn®, Inc. service technician.

Empty pails may be recycled in accordance with your local recycling and waste management requirements. If construction includes deconstruction and reclamation of plastic construction products, it may be necessary to sort plastics according to designations.

Code Compliance	
INTERNATIONAL BUILDING CODE® (IBC®)	
2021	2018
<b>Chapter 8 Interior Finish</b> 803.1.1 Interior Wall and Ceiling Finish Materials NFPA 286 803.1.2 Interior Wall and Ceiling Finish Materials ASTM E84 or UL 723 803.4 Foam Plastics <b>Chapter 26 Plastic</b> 2603.4/2603.9 Thermal Barrier Special Approval 2603.4.1.6 Attics and Crawl Spaces	<b>Chapter 8 Interior Finish</b> 803.1.1 Interior Wall and Ceiling Finish Materials NFPA 286 803.1.2 Interior Wall and Ceiling Finish Materials ASTM E84 or UL 723 803.4 Foam Plastics <b>Chapter 26 Plastic</b> 2603.4/2603.9 Thermal Barrier Special Approval 2603.4.1.6 Attics and Crawl Spaces
2015	2012
<b>Chapter 8 Interior Finish</b> 803.1.1 Interior Wall and Ceiling Finish Material 803.1.2 Corner Test for Interior Wall or Ceiling Finish 803.4 Foam Plastics <b>Chapter 26 Plastic</b> 2603.4/2603.9 Thermal Barrier Special Approval 2603.4.1.6 Attics and Crawl Spaces	<b>Chapter 8 Interior Finish</b> 803.1.1 Interior Wall and Ceiling Finish Material 803.1.2 Corner Test for Interior Wall or Ceiling Finish 803.4 Foam Plastics <b>Chapter 26 Plastic</b> 2603.4/2603.10 Thermal Barrier Special Approval 2603.4.1.6 Attics and Crawl Spaces



Table 3 continued

*Code Compliance*

**INTERNATIONAL MECHANICAL CODE® (IMC®)**

2021	2018
<b>Chapter 6 Duct Systems</b> 602.2 Plenums Construction FSI/SDI	<b>Chapter 6 Duct Systems</b> 602.2 Plenums Construction FSI/SDI
2015	2012
<b>Chapter 6 Duct Systems</b> 602.2 Plenums Construction FSI/SDI	<b>Chapter 6 Duct Systems</b> 602.2 Plenums Construction FSI/SDI

**INTERNATIONAL RESIDENTIAL CODE® (IRC®)**

2021	2018
<b>Chapter 3 Building and Planning</b> R302.9 Flame Spread and Smoke Developed Index for Wall and Ceiling Finishes R316.4/R316.6 Thermal Barrier Specific Approval R316.5.3 (AC377 Appx X) Foam Plastic in Attics R316.5.4 (AC377 Appx X) Foam Plastic in Crawl Spaces	<b>Chapter 3 Building and Planning</b> R302.9 Flame Spread and Smoke Developed Index for Wall and Ceiling Finishes R316.4/R316.6 Thermal Barrier Specific Approval R316.5.3 (AC377 Appx X) Foam Plastic in Attics R316.5.4 (AC377 Appx X) Foam Plastic in Crawl Spaces
2015	2012
<b>Chapter 3 Building and Planning</b> R302.9 Flame Spread and Smoke Developed Index for Wall and Ceiling Finishes R316.4/R316.6 Thermal Barrier Specific Approval R316.5.3 (AC377 Appx X) Foam Plastic in Attics R316.5.4 (AC377 Appx X) Foam Plastic in Crawl Spaces	<b>Chapter 3 Building and Planning</b> R302.9 Flame Spread and Smoke Developed Index for Wall and Ceiling Finishes R316.4/R316.6 Thermal Barrier Specific Approval R316.5.3 (AC377 Appx X) Foam Plastic in Attics R316.5.4 (AC377 Appx X) Foam Plastic in Crawl Spaces

**NATIONAL FIRE PROTECTION ASSOCIATION® (NFPA®) 101**

2018	2015	2012
<b>Chapter 10 Interior Finish</b> 10.2.3 Interior Wall/Ceiling Finish Testing & Classification  10.2.3.4 Required to be Tested ASTM E84 or UL 723  10.2.4.3 Cellular or Foamed Plastic (SIPs) 10.2.4.3.3 Cellular or Foamed Plastic Testing (SIPs)  10.2.4.3.4 Cellular or Foamed Plastic Trim (SIPs) 10.2.6.1 Fire Retardant Coatings FSI/SD	<b>Chapter 10 Interior Finish</b> 10.2.3 Interior Wall/Ceiling Finish Testing & Classification  10.2.3.4 Required to be Tested ASTM E84 or UL 723  10.2.4.3 Cellular or Foamed Plastic (SIPs) 10.2.4.3.1 Cellular or Foamed Plastic Testing (SIPs)  10.2.4.3.2 Cellular or Foamed Plastic Trim (SIPs) 10.2.6.1 Fire Retardant Coatings FSI/SD	<b>Chapter 10 Interior Finish</b> 10.2.3 Interior Wall/Ceiling Finish Testing & Classification  10.2.3.4 Required to be Tested ASTM E84 or UL 723  10.2.4.3 Cellular or Foamed Plastic (SIPs) 10.2.4.3.1 Cellular or Foamed Plastic Testing (SIPs)  10.2.4.3.2 Cellular or Foamed Plastic Trim (SIPs) 10.2.6.1 Fire Retardant Coatings FSI/SD
<b>Chapter 33 Existing Residential Board/Care Occupancies</b> 33.2.3.5.7.2(4)/1.4 Attics	<b>Chapter 33 Existing Residential Board/Care Occupancies</b> 33.2.3.5.7.2(4)/1.4 Attics	<b>Chapter 33 Existing Residential Board/Care Occupancies</b> 33.2.3.5.7.2(4)/1.4 Attics

Table 4

*Green Standards*

**ANSI/ASHRAE/ICC/USGBC STANDARD 189.1**

2017	2014
<b>8. Indoor Environmental Quality (IEQ)</b> 8.4.2.2 Paints and Coatings 8.4.2.2.1 Emissions Requirements 8.4.2.2.2 VOC Content Requirements: a and b 8.5.2 Materials	<b>8. Indoor Environmental Quality (IEQ)</b> 8.4.2.2 Paints and Coatings 8.4.2.2.1 Emissions Requirements 8.4.2.2.2 VOC Content Requirements 8.5.2 Materials
<b>9. The Buildings Impact on the Atmosphere, Materials, and Resources</b> 9.3.1.1 Diversion 9.3.1.2 Total Waste 9.3.1.3 Construction Waste Management Plan	<b>9. The Building's Impact on the Atmosphere, Materials, and Resources</b> 9.3.1.1 Diversion 9.3.1.2 Total Waste 9.3.1.3 Construction Waste Management Plan

**CALIFORNIA AIR RESOURCES BOARD (ARB)**

2008

<b>8. Compliance and Test Methods</b> 8.1 Calculation of VOC Content 8.2 VOC Content of Coatings	8.5.9 VOC Content of Coatings Table 1, VOC Content Limits for Architectural Coatings: Flat Coatings
--	--

**CALIFORNIA DEPARTMENT OF PUBLIC HEALTH (CDPH)**

2017	2010
<b>STANDARD METHOD FOR THE TESTING AND EVALUATION OF VOC EMISSIONS FROM INDOOR SOURCES USING ENVIRONMENTAL CHAMBERS V1.2 California Specification 01350</b>	<b>STANDARD METHOD FOR THE TESTING AND EVALUATION OF VOC EMISSIONS FROM INDOOR SOURCES USING ENVIRONMENTAL CHAMBERS V1.1 CA Specification 01350</b>
<b>COLLABORATIVE FOR HIGH PERFORMANCE SCHOOLS (CHPS)</b>	

2017	2016
<b>Core Criteria New Construction and Renovation</b> <b>Indoor Environmental Quality</b> Prerequisite: EQ 7.0 Low Emitting Materials/Paints & Coatings EQ 7.1 Additional Low Emitting Materials/EQ 7.1.5 Paints & Coatings	<b>Core Criteria New Construction and Renovation</b> <b>Indoor Environmental Quality</b> Prerequisite: EQ 7.0 Low Emitting Materials/Paints & Coatings EQ 7.1 Additional Low Emitting Materials/EQ 7.1.5 Paints & Coatings
<b>Materials &amp; Waste Management</b> Prerequisite MW 1.0 Storage & Collection Recyclables	<b>Materials &amp; Waste Management</b> Prerequisite MW 1.0 Storage & Collection Recyclables



**Made in the USA**



Table 4 continued	
Green Standards	
GENERAL SERVICES ADMINISTRATION (GSA) PUBLIC BUILDING SERVICE (PBS) - P100	
2017	2016
<b>Chapter 3 Architecture and Interior Design</b> 3.5.2.19 Interior Coatings (Paint) <b>Chapter 4 Prescriptive Structural Engineering</b> 4.3.1 Innovative Materials and Methods <b>Chapter 7 Fire Protection</b> 7.1.3.3 Alternative Designs 7.15 Performance-Based Design	<b>Chapter 3 Architecture and Interior Design</b> 3.5.2.19 Interior Coatings (Paint) <b>Chapter 4 Structural Engineering</b> 4.3.1 Innovative Materials and Methods <b>Chapter 7 Fire Protection and Life Safety</b> 7.3.1.3 Alternative Designs 7.15 Performance-Based Design
ICC/ASHRAE 700 NATIONAL GREEN BUILDING STANDARD™ (NGBS)	
2015	2012
<b>Chapter 6 Resource Efficiency</b> 605.3 Recycled Construction Materials 609.1 Regional Materials <b>Chapter 9 Indoor Environmental Quality</b> 901.8 Wall Coverings 901.9 Interior Architectural Coatings 901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 901.9.3 904.1 Indoor Air Quality (IAQ) During Construction 904.2 Indoor Air Quality (IAQ) Post Construction	<b>Chapter 6 Resource Efficiency</b> 605.3 Recycled Construction Materials 609.1 Regional Materials <b>Chapter 9 Indoor Environmental Quality</b> 901.8 Wall Coverings 901.9 Interior Architectural Coatings 901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 901.9.3
ANSI/ASHRAE/ICC/USGBC STANDARD 189.1	
2015	2012
<b>Chapter 11 Remodeling</b> 11.605.3 On-site Recycling 11.605.4 Recycled Construction Materials 11.609.1 Regional Materials 11.901.8 Wall Coverings 11.901.9 Interior Architectural Coatings 11.901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 11.901.9.3 11.901.9.4 Mandatory Requirement 11.904.1 Indoor Air Quality (IAQ) During Construction 11.904.2 Indoor Air Quality (IAQ) Post Construction <b>Chapter 12 Remodeling of Functional Areas</b> 12.1(A).609.1 Regional Materials 12.1.901.8 Interior Wall Coverings 12.1.901.9 Architectural Coatings 12.1.901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 12.1.901.9.2	<b>Chapter 11 Remodeling</b> 11.605.3 On-site Recycling 11.605.4 Recycled Construction Materials 11.609.1 Regional Materials 11.901.8 Wall Coverings 11.901.9 Interior Architectural Coatings 11.901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 11.901.9.3 11.901.9.4 Mandatory Requirement <b>Chapter 12 Remodeling of Functional Areas</b> 12.1(A).609.1 Regional Materials 12.1.901.8 Interior Wall Coverings 12.1.901.9 Architectural Coatings 12.1.901.9.1 VOC Content Limits Architectural Coatings Flat Coatings or 12.1.901.9.2
INTERNATIONAL GREEN CONSTRUCTION CODE® (IgCC®)	
2018	2018
<b>8. Indoor Environmental Quality (IEQ)</b> 8.4.2.2 Paints and Coatings 8.4.2.2.1 Emissions Requirements 8.4.2.2.2 VOC Content Requirements: a and b 8.5.2 Materials <b>9. The Buildings Impact on the Atmosphere, Materials, and Resources</b> 9.3.1.1 Diversion 9.3.1.2 Total Waste 9.3.1.3 Construction Waste Management Plan 9.4.1.2 Regional Materials	<b>Chapter 5 Material Resource Conservation and Efficiency</b> 503.1 Construction Material and Waste Management Plan  <b>Chapter 8 Indoor Environmental Quality and Comfort</b> 806.3 Architectural Paints and Coatings/Table 806.3(1) or 806.3(2)





Plus ThB

Intumescent Coating  
Spray Polyurethane Foam Insulation

Table 4 continued

Green Standards

U.S. GREEN BUILDING COUNCIL® LEED®

v4 2018

v3 2009

**BUILDING DESIGN (BD) AND CONSTRUCTION (C)**

**Materials and Resources (MR)**

- MR Prerequisite: Storage and Collection of Recyclables
- MR Credit: Building Life-Cycle Impact Reduction: Option 1 or Option 2
- MR Credit: Building Product Disclosure and Optimization- Material Ingredients: Option 2 International Alternative Compliance Path- Reach Optimization
- MR Credit: Construction and Demolition Waste Management

**Indoor Environmental Quality (EQ)**

- EQ Credit: Low-Emitting Materials: Option 1

**Innovation in Design (ID)**

- Credit 1 Innovation in Design

**HOMES DESIGN (HD) and CONSTRUCTION (C)**

**Materials and Resources (MR)**

- MR Credit: Construction Waste Management

**Indoor Environmental Quality (EQ)**

- EQ Credit: Low-Emitting Products

**INTERIOR DESIGN (ID) and CONSTRUCTION (C)**

**Materials and Resources (MR)**

- MR Prerequisite: Storage and Collection of Recyclables
- MR Credit: Building Product Disclosure and Optimization- Material Ingredients: Option 2 International Alternative Compliance Path- Reach Optimization
- MR Credit: Construction and Demolition of Waste Management

**Indoor Environmental Quality (EQ)**

- EQ Credit: Low-Emitting Materials: Option 1

**Innovation in Design (ID)**

- Credit 1 Innovation in Design

**NEW CONSTRUCTION AND MAJOR RENNOVATIONS**

**Materials and Resources (MR)**

- MR Credit 1.1 Building Reuse- Maintain Existing Walls, Floors & Roofs
- MR Credit 1.2 Building Reuse- Maintain Interior Nonstructural Elements
- MR Credit 2 Construction Waste Management
- MR Credit 5 Regional Materials

**Indoor Environmental Quality (IEQ)**

- IEQ Credit 4.2 Low Emitting Materials- Paints & Coatings

**Innovation in Design (ID)**

- Credit 1 Innovation in Design

SOUTH COAST AIR QUALITY MANAGEMENT DISTRICT (SCAQMD) RULE 1113

2016

2013

**Table of Standards 1, VOC Limits**

- Flats
- (e) Test Methods
- (e)(1)(A) U.S. EPA Reference Test Method 24

**Table of Standards 1, VOC Limits**

- Flats
- (e) Test Methods
- (e)(1)(A) U.S. EPA Reference Test Method 24

No-Burn, Inc.

**SALES INFORMATION AND ORDER PLACEMENT**

1-800-989-8577

**TECHNICAL INFORMATION**

1-800-989-8577

[www.noburn.com](http://www.noburn.com)

© 2023 No-Burn, Inc.

**TRADEMARKS** No-Burn, No-Burn logo and Fire Wise are trademarks owned by or licensed to No-Burn®, Inc.

**LIMITED WARRANTY** No-Burn®, Inc. warrants that the No-Burn® formula will be manufactured to the same specifications and quality, and will perform equally to the tests performed by the independent laboratories when properly applied. Warranty coverage is limited solely to the cost of product purchased hereunder and specifically excludes incidental expenses and consequential damages. The applicator warrants that the product, in its original form from the manufacturer, will be stored, mixed and/or applied as directed in the guidelines published by No-Burn®, Inc., to every reasonably accessible area that has been specified for protection. All implied warranties, from No-Burn®, Inc. or the applicator are excluded. There may be situations and materials for which No-Burn® will not prevent a fire from igniting or retard the progress of a fire.

**POLICY & PROCEDURES** All sales of this product by No-Burn, Inc. are subjected to our Policy & Procedures available at <http://noburn.com/policies-procedures>

**UPDATES AND CURRENT INFORMATION** Revised 22-December-2023. The information in this document may change without notice.



Made in the USA



Technical Data Sheet

CSI 09 96 46

#### FABRICANTE

No-Burn, Inc.  
1255 High Street, Suite 200,  
Wadsworth, Ohio 44281  
[www.noburn.com](http://www.noburn.com)

#### DESCRIPCIÓN

No-Burn® Plus ThB es un recubrimiento intumescente de película delgada a base de agua que, cuando se expone a altas temperaturas y a llamas, se hincha y se carboniza para crear una barrera aislante que protege los *Sustratos* tratados del fuego. Este material está certificado para aplicarse en una gran variedad de *Sustratos* y la conformidad con la reacción al fuego se logra con el adecuado espesor de película húmeda.

#### 1. PRINCIPALES USOS

Plus ThB se puede usar en edificios nuevos y existentes, de conformidad con las normas IBC®, IMC®, IRC®, IEBC® y otros códigos o normas aplicables, y se utiliza en aplicaciones donde se ofrece:

- Clasificación de acabado interior clase I o clase A: F5 0 / SD 10
- Barrera térmica alternativa o no prescriptive
- Barrera de ignición alternativa o no prescriptiva
- Resistencia al vapor de Clase III
- Montaje de pared exterior nominal

Informes de evaluación de cumplimiento de códigos: [ER 305](#) & [TER 1905-03](#).  
Verificación de instalación: [SPFA-148](#).

Listado de diseños de Intertek: [BASF/FI 30-90](#).

#### 2. ESPECIFICACIONES

Color:	Blanco/Gris/Tintado <a href="#">Rueda de color intumescente y tintado</a>		
	Blanco	Gris	Tintado

Acabado:	Plano
Contenido de químicos orgánicos volátiles:	18 g/l método EPA 24
Tiempo de secado:	De 60 a 90 minutos
Cubetas:	5 galones (19 l), 58.5 lbs
Tambores:	tambor de 55 galones (208 l), neto 45 galones (170 l) 586.5 lbs
Vida útil:	12 meses
Tiempo de curado:	24 horas
Punto de ebullición:	212 °F (97.7 °C)
Punto de congelamiento:	32 °F (0 °C)
% volátil por volumen:	36%
Gravedad específica:	1.25

Consultar la [ficha de datos de seguridad \(MSDS\)](#) y [Prácticas recomendadas para el manejo seguro y el almacenamiento](#) del producto para obtener información adicional.

#### 3. RENDIMIENTO DEL PRODUCTO

No-Burn® Plus ThB puede usarse para los usos principales expresados. Como componente de un conjunto de barrera de ignición alternativa o conjunto de barrera térmica, Plus ThB es un revestimiento intumescente contra incendios para espacios interiores donde se instala espuma de poliuretano en aerosol. Aplicado en una aplicación de una sola capa, Plus ThB protege de forma pasiva la superficie de espuma en aerosol al retrasar el aumento de temperatura de la espuma y al retrasar o evitar que la espuma se encienda. Aplicable para espuma de poliuretano en spray de células cerradas y células cerradas, Plus ThB proporciona

protección contra incendios y retardancia a la vaporización de Clase III según lo exige el código para la construcción residencial, comercial y comercial. Cumple con los requisitos del USDA para contacto incidental con alimentos y materiales ANSI / NSF 51 para la zona de alimentos.

#### 4. NORMAS APLICABLES

No-Burn® Plus ThB puede ser especificado en el cumplimiento de los siguientes:	
AC377	EC017
AC456	GSA PBS-P100
Normas ANSI/ASHRAE/ICC/USGBC 189.1	ICC/ASHRAE 700 NGBS
Normas ANSI/NSF 51	IgCC
ASTM E84	LEED v3 2009 & v4
ASTM E96	NFPA 285
CARB	NFPA 286
CDPH (CA Spec 01350)	SCAQMD Regla 1113
CHPS	UL 1715

Tabla 1

Material	Sustrato		
	TB <sup>1</sup> or IB <sup>2</sup>	Grosor de Película	Índice de propagación
Accufoam CC Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Accufoam CC-HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
AMBIT AMBI_SEAL 5.0 Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
AMBIT Ambi-Tite 201 (245Fa) Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
AMBIT Ambi-Tite 204 HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Alpha Polymers AP 100 (OC) Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Alpha Polymers AP 200 245fa (CC) Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
AMD Diamondback Célula Cerrada SPF	TB	16 húmedo	100 sq. ft./gal.
BASF Enertite® G Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Enertite® Max Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® SP Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® 158 Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® 178 Célula Cerrada SPF	TB	17 húmedo	94 sq. ft./gal.
BASF Spraytite® 81206 Célula Cerrada SPF	TB	17 húmedo	94 sq. ft./gal.
BASF Walltite® US Célula Cerrada SPF	TB	17 húmedo	94 sq. ft./gal.
BASF Spraytite® Comfort Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® Comfort XL Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® LWP-L Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Spraytite® LWP Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Walltite® MAX Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Walltite® XL Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
BASF Walltite® Plus Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate 50 HY Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro High Yield Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro XTR Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate 50 ES Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate 50 Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro No Mix Celda Abierta SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate HFO 2.0 Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle SealTite Pro One Zero Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Carlisle Foamsulate HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Central Urethane X-Press Seal 170 Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Central Urethane X-Press Seal 200 Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Creative Polymer Solutions Accufoam CC Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Creative Polymer Solutions Accufoam 2.0 CC-HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Elastochem Insulthane 200 Evolution Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.
Elastochem Insulthane Extreme HFO Célula Cerrada SPF	TB	14 húmedo	115 sq. ft./gal.



Made in the USA







Plus ThB

Intumescent Coating

Spray Polyurethane Foam Insulation

Table with columns for product name, application code, thickness, and coverage. It lists various products like Elastochem Insulthane, Huntsman, and BASF, with their respective application codes (e.g., TB, IB) and coverage values (e.g., 14 húmedo, 115 sq. ft./gal.).



Made in the USA



Technical Data Sheet

Carlisle Foamsulate 50 HY Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Carlisle SealTite Pro XTR Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Carlisle Foamsulate 50 ES Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Carlisle SealTite Pro High Yield Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Carlisle Foamsulate 50 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Carlisle SealTite Pro No Mix Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Creative Polymer Accufoam® Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
DAP Touch N' Seal 2.2 PCF Célula Cerrada SPF	IB	8 húmedo	200 sq. ft./gal.
Franklin Titebond Weathermaster Superfoam Célula Cerrada SPF	IB	10 húmedo	160 sq. ft./gal.
Gaco Western EZSpray F4500 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Holcim SES EasySeal ULD Spray Foam Insulation	IB	6 húmedo	267 sq. ft./gal.
Huber ZIP Systems R-Sheating Panel (R-3 & R-6)	IB	10 húmedo	160 sq. ft./gal.
Huntsman (Demilec) Sealection® 500 Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Demilec) Sealection® NIM Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Demilec) Agribalance® Célula Abierta	IB	10 húmedo	160 sq. ft./gal.
Huntsman (Icynene) Classic Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Icynene) Classic Ultra Select Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Icynene) Classic Plus Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Icynene) Prime Gold Célula Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Icynene) MD-C-200 Célula Cerrada SPF	IB	16 húmedo	100 sq. ft./gal.
Huntsman (Icynene) ProSeal Eco (MD-R-200) Célula Cerrada SPF	IB	5 húmedo	320 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 450 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Huntsman (Lapolla) Foam-Lok FL 750 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
ICP Handi-Foam HVLP LD Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
ICP Handi-Foam® E-84 Clase 1(A) Célula Cerrada SPF	IB	10 húmedo	160 sq. ft./gal.
John Manville JM Corbond HY Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
NSF Polymers OC-OG Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
NSF Polymers OC 365 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
SES EasySeal ULD Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
SES EasySeal 0.5 Celda Abierta SPF	IB	5 húmedo	320 sq. ft./gal.
SWD Quik-Shield 106 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
ThermoSeal TS 360 Celda Abierta SPF	IB	4 húmedo	401 sq. ft./gal.
ThermoSeal TS 500 Celda Abierta SPF	IB	4 húmedo	401 sq. ft./gal.
ThermoSeal TS 800 Celda Abierta SPF	IB	4 húmedo	401 sq. ft./gal.
ThermoSeal OX Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.
Tiger Foam® E-84 Clase 1 SPF	IB	10 húmedo	160 sq. ft./gal.
Victory Polymers VPC-50 Celda Abierta SPF	IB	6 húmedo	267 sq. ft./gal.

<sup>1</sup> Conjuntos alternativos de barrera térmica (TB): ER 305 Tabla 2 & TER 1905-03 Tabla 1

<sup>2</sup> Conjuntos alternativos de barrera de ignición (IB): ER 305 Tabla 3 & TER 1905-03 Tabla 2

## 5. EQUIPO

Los métodos de aplicación pueden incluir atomizadores sin aire (airless), rodillo o brocha. Los fabricantes de *Equipos* y los modelos de *Equipo* atomizador de aplicador sin aire (airless) varían y a continuación presentamos ejemplos de *Equipos* aplicables. Las recomendaciones de los *Equipos* atomizadores de aplicador sin aire (airless) contienen enlaces a las especificaciones del fabricante para referencia.

Tabla 2		
Equipo		
Fabricante	Modelo	
Graco®	<a href="#">Ultra Max II 795</a>	<a href="#">Ultra Max II 1595</a>
	<a href="#">Ultra Max II 1095</a>	<a href="#">TexSpray Mark V</a>
Titan®	<a href="#">Impact™ 840</a>	<a href="#">PowrTwin™ 6900 Plus</a>
	<a href="#">Impact™ 1140</a>	<a href="#">PowrTwin™ 8900 Plus</a>

Recomienda usar boquillas con orificio de tamaño 0.019 a 0.025 y manguerapara atomizadores sin aire (airless) tengan un diámetro interior de ¼" o superior.

El Equipo atomizador debe ser capaz de producir un mínimo de 3,300 psi y los tamaños de boquilla recomendados son 419-425 o 519-525. Se recomienda quitar los filtros de la pistola atomizadora para permitir el paso del contenido sólido. No retire la protección contra rocas (pantalla) de la parte inferior del tubo de admisión. Se recomienda que las manguerapara atomizadores sin aire (airless) tengan un diámetro interior

de ¼" o superior. Probablemente se requieran variaciones en el ancho del patrón de atomizado y el tamaño de la boquilla según el área expuesta y el *Sustrato(s)* donde se aplica el producto. La limpieza de los *Equipos* se puede llevar a cabo con agua, u otros métodos recomendados por el fabricante del *Equipo*.

## 6. PROTECCIÓN PERSONAL Y CONTROLES DE EXPOSICIÓN

Se recomienda usar un respirador certificado y gafas de seguridad para evitar el rociado y salpicaduras. La protección para los ojos y la cara debe estar en conformidad con la norma OSHA 29 CFR 1910.133. Se recomienda usar guantes de goma o plástico para la protección de manos y brazos. La limpieza personal puede ser con agua y jabón.

Si se aplica con atomizador, utilizar un respirador con purificador de aire aprobado por NIOSH de conformidad con la norma OSHA 29 CFR 1910.134 (d)(1)(ii). Si se utiliza en un área limitada, se recomienda utilizar un respirador con purificador de aire de cara completa (PAPR) o un respirador con suministro de aire (SAR). Utilizar los respiradores de conformidad con las normas 29 CFR 1910.134 (d)(3)(i) (A) Cuadro 1, 29 CFR 1910.134(d)(3)(iii)(B) y 29 CFR 1910.134(d)(3)(iv)(B).

Utilizar controles de ingeniería adecuados, como una ventilación adecuada. Cuando estos sistemas no son eficaces, se debe usar equipo de protección personal adecuado, que funcione de manera satisfactoria y cumpla con la norma OSHA u otras normas reconocidas.

## 7. MEZCLA, PINTADO Y SOBRETUBOS

Plus ThB debe mezclarse completamente antes de su uso de acuerdo con las recomendaciones del fabricante. Mezcle con una varilla mezcladora eléctrica de 5 galones a 800-1200 RPM o entre 800 y 1200 RPM hasta que esté completamente mezclado. Agitar No-Burn® Plus ThB con un agitador de pintura NO es suficiente. No se recomienda filtrar o filtrar Plus ThB. Si No-Burn® Plus ThB se mezcla más de 24 horas antes de usarlo, vuelva a mezclarlo de acuerdo con las instrucciones del fabricante. Generalmente no se necesita adelgazar; Si Plus ThB ha estado expuesto a altas temperaturas, el agua puede evaporarse del contenedor plástico de 5 galones. Si el nivel de pintura está por debajo de 3-4 pulgadas desde la parte superior del recipiente, agregue suficiente agua para que el nivel vuelva a estar a 3 pulgadas de la parte superior para garantizar la consistencia adecuada. Mezcle Plus ThB nuevamente de acuerdo con las instrucciones del fabricante.

Después de mezclar, si la viscosidad sigue siendo demasiado alta, puede agregar 8 onzas de agua por cubo de 5 galones y mezclar para reducir la viscosidad. Mezcle Plus ThB nuevamente de acuerdo con las instrucciones del fabricante. Tenga cuidado de no agregar demasiada agua o el producto podría correr y gotear durante la aplicación.

Plus ThB nunca debe permitirse que se congele a 32 ° F (0 ° C), almacenado entre 40 ° F y 90 ° F (4.4 ° C y 32.2 ° C), y se mantenga alejado de la luz solar directa; Si no puede verificar que se han mantenido estas condiciones, el producto se puede desechar de acuerdo con la FDS (M) del fabricante.

Si se desea teñir, Plus ThB se puede teñir a una velocidad máxima de 2 oz. de tinte por galón con tinte disponible comercialmente que sea seguro para usar con pinturas a base de agua. Se recomienda utilizar No-Burn® Black Tint, fabricado por No-Burn, Inc., para teñir. No-Burn® Black Tint se puede agregar a razón de 12 oz por cubo de 5 galones.



Comuníquese con el fabricante para obtener información adicional sobre tintes.

Cuando se desea un color específico o negro, se puede utilizar una capa superior a base de agua con un pH de 7 a 8 (es decir, Sherwin Williams A-100 o Behr Premium Plus). Antes de usar cualquier capa, se recomienda probar la compatibilidad en un área discreta antes de una aplicación generalizada. La compatibilidad se puede considerar como la condición general satisfactoria del(los) sustrato(s) una vez que se hayan aplicado No-Burn® Plus ThB y una capa superior. No-Burn® Inc. no ofrece garantías de coincidencia de colores cuando se utiliza un tinte de un fabricante externo.

## 8. APLICACIÓN

Al aplicar No-Burn® Plus ThB, el recubrimiento debe aplicarse al *Sustrato(s)*, según corresponda, de acuerdo con el Informe de evaluación (ER) 305, Informe de evaluación (TER) 1905-03 y / o las hojas de datos técnicos del fabricante. Copias de datos técnicos relevantes y / o documentos estarán disponibles en el lugar de trabajo.

Antes y durante la aplicación del recubrimiento, las superficies del *Sustrato(s)* deberán estar secas, limpias y libres de suciedad, polvo, aceite, grasa, y todo material de recubrimiento anterior, como son pinturas, tintes y selladores. La espuma debe dejarse enfriar a temperatura ambiente antes de la aplicación de No-Burn® Plus ThB, por lo menos 1 hora. El *Sustrato(s)* no debe tener, ni haber sido expuesto a, tratamientos, sustancias químicas, recubrimientos, etc. antes de la aplicación de Plus ThB. La observación visual de un recubrimiento intumescente es de un distintivo color blanco por naturaleza. Para la verificación del espesor aplicado en húmedo, se debe usar un medidor de espesores estándar para pintores durante la aplicación. El espesor del producto seco será de 0.55 a 0.70 veces el espesor húmedo. Plus ThB se aplicará en los *Sustrato(s)*, según corresponda, de conformidad con las recomendaciones del fabricante. Los *Sustrato(s)* deberán estar en su posición final en el edificio, expuestos directamente al interior, protegidos de la intemperie, en lugares acondicionados y no acondicionados. Además, Plus ThB se aplicará en las zonas dentro de la membrana impermeabilizante o superficies no expuestas a la intemperie.

Las temperaturas de la superficie y la ambiental antes y durante la aplicación será de al menos 40 °F (4.4 °C). Las temperaturas de superficie no deben exceder de 100 °F (37.7 °C) durante la aplicación. El recubrimiento se aplicará en una tasa de aplicación establecida mediante atomización, rodillo o pincel.

El tiempo de secado es típicamente de 60 a 90 minutos y el tiempo de curado es de 24 horas como mínimo, aunque depende de la temperatura

ambiente y la humedad relativa. Si es necesario aplicar más de una capa, deje secar el No-Burn® Plus ThB completamente entre capas.

Siempre es mejor seguir ante todo las directrices de SPF Manufacturer cuando se trata de instalar Plus ThB, siguiendo estrictamente las instrucciones de instalación de rociado. En caso de temperaturas elevadas, humedad o frío extremo, las directrices de Plus ThB son las siguientes.

A. Plus Thb se puede instalar en un SPF recién instalado según los tiempos de aplicación de la capa superior del fabricante del SPF. Consulte la información de datos técnicos del SPF al que se aplicará Plus Thb. Siga atentamente las instrucciones de instalación del fabricante del SPF.

B. Las temperaturas ideales de instalación son 65 grados Fahrenheit o más y menos del 65 % de humedad relativa.

C. La temperatura ambiente del aire y del sustrato DEBE ser superior a 40 grados Fahrenheit para aplicar Plus Thb y no puede bajar de 40 grados Fahrenheit hasta que Plus Thb se haya secado al tacto.

D. Durante al menos 72 horas después de la instalación de Plus ThB, se deben mantener temperaturas constantes dentro de los parámetros de instalación (al menos 40 grados Fahrenheit, preferiblemente 65 grados Fahrenheit o más) y no más del 65% de humedad relativa con lecturas tomadas diariamente. Cualquier condición fuera de estas pautas debe ser aprobada por el servicio técnico de No-Burn®, Inc.

E. El espacio donde se esté instalando Plus Thb debe estar bien ventilado, ya sea por aberturas naturales o con el uso de equipos de ventilación mecánica, tanto durante la instalación como por hasta 72 horas una vez finalizada la instalación, para permitir que se complete el proceso de curado. La humedad del aire ambiente y la cantidad de flujo de aire a través del espacio afectarán los tiempos de curado (es decir, más húmedo con menos movimiento de aire tomará más tiempo para curar).

F. Una vez curado, Plus Thb instalado en ambientes continuos de alta humedad requerirá una capa superior como pintura exterior Behr Premium Plus o Sherwin Williams A-100 (es decir, 70% de humedad y más). Las estructuras de estacionamiento, tanto por encima como por debajo del nivel del suelo, requerirán esta protección. Si el instalador tiene alguna pregunta sobre los niveles de humedad del ambiente una vez instalado Plus Thb, se recomienda que hable con un técnico de servicio de No-Burn®, Inc.

Los cubos vacíos se pueden reciclar de acuerdo con los requisitos locales de reciclaje y gestión de residuos. Si la construcción incluye la deconstrucción y recuperación de productos plásticos de construcción, puede ser necesario clasificar los plásticos según sus designaciones.

No-Burn, Inc.  
**INFORMACIÓN DE VENTAS Y PEDIDOS**  
1-800-989-8577  
**INFORMACIÓN TÉCNICA**  
1-800-989-8577  
[www.noburn.com](http://www.noburn.com)

© 2023 No-Burn, Inc.

MARCAS COMERCIALES No-Burn, el logotipo de No-Burn y Fire Wise son marcas comerciales propiedad de No-Burn®, Inc. o con licencia de No-Burn®, Inc.

**GARANTÍA LIMITADA** No-Burn®, Inc. garantiza que la fórmula No-Burn® se fabricará con las mismas especificaciones y calidad, y se comportará de forma similar a las pruebas realizadas por los laboratorios independientes cuando se aplica correctamente. La cobertura de la garantía se limita únicamente al costo del producto adquirido a continuación y excluye específicamente los gastos imprevistos y los daños consecuentes. El aplicador garantiza que el producto, en su forma original del fabricante, se almacenará, mezclará y / o aplicará como se indica en las pautas publicadas por No-Burn®, Inc., a cada área razonablemente accesible que se haya especificado para protección. Se excluyen todas las garantías implícitas de No-Burn®, Inc. o del aplicador. Puede haber situaciones y materiales para los cuales No-Burn® no evitará que un incendio encienda o retarde el progreso de un incendio.

**POLÍTICA Y PROCEDIMIENTOS** Toda venta de este producto por parte de No-Burn, Inc. están sujeta a nuestra política y procedimientos disponibles en <http://noburn.com/polices-procedures>

**NOTICIAS E INFORMACIÓN ACTUAL** Revisado 22-Diciembre-2023. La información contenida en este documento puede cambiar sin previo aviso.



Made in the USA



Technical Data Sheet

CSI 09 96 46